

product name		Production location		
Schwarzburg B-Loch		Oberlausitz		
Colour				
No description				
Format				
Moulding method Wirecut				
RF: 250 x 120 x 65 mm	From one series to an	nother, the average size may slightly differ.		
Essential Characteristics - EN771-1				
Dimensions: tolerance category	T2			
Dimensions: range category	R1			
Active soluble salt	S2			
Average compressive strength	>= 43,8 N/mm²	Tested to the bed face		
Normalised compressive strength	>=31 N/mm²	Tested to the bed face		
Dimensional stability	NPD			
Bond Strength general	0,15 N/mm ²	Value according EN998-2 Annex C		
Adhesive strength (mortar)	0,30 N/mm ²	Value according EN998-2 Annex C		
Reaction to fire	A1	Category		
Water absorption	<= 6% m/md			
Water vapour permeability	50/100			
Net dry density	2300 kg/m³ (D2)			
Gross dry density	1500 kg/m³ (D2)			
Equivalent thermal conductivity	<=NPD	Value according EN1745, Annex A 50%		
Freeze/thaw resistance	F2			
Dangerous substances	NL-BSB	According Annex ZA.3		
Other Characteristics				
Initial rate of water absorption - Non-coated Brick	NPD	Value according EN771-1:2011 - 5.3.8		

Other Characteristics			
Initial rate of water absorption - Non-coated Brick	NPD	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption (kg/m².min) - Coated Brick*	NPD	Value according EN771-1:2011 - 5.3.8	
Eq. Thermal Property 10, dry mass (90/90)	NPD		
Eq. Thermal Property 10, dry mass (lambda Ui)	NPD		
Eq. Thermal Property 10, dry mass (lambda Ue)	NPD		
	· · · · · · · · · · · · · · · · · · ·		











Storage & handling	Cutting
- Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines	Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).

*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.