



product name		Production location
Wasserstrich Sintra		Beek
Een mengsel van Eifel- en Westerwaldklei vormt de basis. Dit mengsel is uitermate geschikt voor de productie van gevelstenen. Door de toepassing van de Wasserstrich techniek krijgen de zichtvlakken van de gevelsteen een generfd en onbezand uitzicht.		
Colour		
Ivory with shades of light brown		
Format		
Moulding method		Waterstruck
WF: 209 x 99 x 50 mm DF: 217 x 100 x 66 mm		From one series to another, the average size may slightly differ.
Essential Characteristics - EN771-1		
 0620-CPR-53104/07		
Dimensions: tolerance category	T2	
Dimensions: range category	R1	
Active soluble salt	S2	
Average compressive strength	$\geq 25 \text{ N/mm}^2$	Tested to the bed face
Normalised compressive strength	$\geq 20 \text{ N/mm}^2$	Tested to the bed face
Dimensional stability	NPD	
Bond Strength general	$0,15 \text{ N/mm}^2$	Value according EN998-2 Annex C
Adhesive strength (mortar)	$0,30 \text{ N/mm}^2$	Value according EN998-2 Annex C
Reaction to fire	A1	Category
Water absorption	$\leq 10\% \text{ m/md}$	
Water vapour permeability	50/100	
Net dry density	$1900 \text{ kg/m}^3 \text{ (D1)}$	
Gross dry density	$1750 \text{ kg/m}^3 \text{ (D1)}$	
Equivalent thermal conductivity	$\leq 0,53 \text{ W/m.K}$	Value according EN1745, Annex A 50%
Freeze/thaw resistance	F2	
Dangerous substances	NL-BSB	According Annex ZA.3
Other Characteristics		
Initial rate of water absorption - Non-coated Brick	$0,5 - 1,5 \text{ kg/m}^2 \cdot \text{min (IW2)}$	Value according EN771-1:2011 - 5.3.8
Initial rate of water absorption ($\text{kg/m}^2 \cdot \text{min}$) - Coated Brick*	NPD	Value according EN771-1:2011 - 5.3.8
Eq. Thermal Property 10, dry mass (90/90)	NPD	
Eq. Thermal Property 10, dry mass (λ_{Di})	NPD	
Eq. Thermal Property 10, dry mass (λ_{De})	NPD	
		
Storage & handling		Cutting
<ul style="list-style-type: none"> - Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines 		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).
<small>*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.</small>		