

| Product name   | Product                     | group   | <b>Production location</b>      |
|--|-----------------------------|---|---------------------------------|
| Blenheim Red Multi   | D1                          | D1 He   |                                 |
| The raw materials are excavated in Weichsel loam layers, the       | local loam of Aeolian       | origin dating fro   | m the Ice Age. This löss mainly |
| consists of a silt-like fraction, suited ideally for the manufactu | uring of hand form bric     | ks. By using spe  | cific sand types for surface    |
| covering, the desired colour is achieved.                          |                             |   |                                 |
| 6  | Colour                      |   |                                 |
| Red brown facing brick with dark shades                            |                             |   |                                 |
|  | Format                      |   |                                 |
| Moulding met   | hod Hand form               |   |                                 |
| DF: 215 x 103 x 66 mm  |                             |   |                                 |
|  |                             | Between batches the average size and color may slightly differ. |                                 |
| Essential Cha  | aracteristics - EN771-1     |   |                                 |
| <b>EN 771-1 - 0620-CPR-97880</b>                                   |                             | UK<br>CA<br>EN 771 - 1855-CPR-24912                             |                                 |
| 2+   |                             | 2.  | +                               |
| Dimensional tolerances   | T2                          |   |                                 |
| Range  | R1                          |   |                                 |
| Active Soluble Salts   | S2                          |   |                                 |
| Mean Compressive strength  | >= 10 N/mm <sup>2</sup>     | Tested to the bed face  |                                 |
| Normalized Compressive strength                                    | >= 10 N/mm²                 | Tested to the bed face  |                                 |
| Dimensional stability  | NPD                         |   |                                 |
| Bond Strength general  | 0,15 N/mm²                  |   |                                 |
| Bond Strength thin layer   | 0,30 N/mm²                  |   |                                 |
| Reaction to fire   | A1                          | Category  |                                 |
| Water absorption   | <= 15% m/md                 |   |                                 |
| Water vapour permeability  | 5/10                        |   |                                 |
| Net dry density  | 1800 kg/m <sup>3</sup> (D1) |   |                                 |
| Gross dry density  | 1780 kg/m <sup>3</sup> (D1) |   |                                 |
| Thermal conductivity Lambda 50/50                                  | <=0,49 W/m.K                |   |                                 |
| Durability against freeze thaw                                     | F2                          |   |                                 |
| Dangerous substances   | NL-BSB                      | According to A  | nnex ZA 3                       |
| Other  | Characteristics             |   |                                 |
| Initial rate of water absorption - Non-coated Bricks               | 1,5 - 4,0 kg/m².min         | Value according EN771-1:2011 - 5.3.8                            |                                 |
|  | (IW3)                       |   |                                 |
| Initial rate of water absorption - Coated bricks                   | 1,5 - 4,0 kg/m².min         | Value according EN771-1:2011 - 5.3.8                            |                                 |
|  | (IW3)                       |   |                                 |
| Freeze/thaw resistance - PTV 23-002                                | NPD                         | NBN 27-009  |                                 |
| Thermal conductivity Lambda 90/90                                  | NPD                         |   |                                 |
| Thermal conductivity Lambda Ui                                     | NPD                         |   |                                 |
| Thermal conductivity Lambda Ue                                     | NPD                         |   |                                 |
|  |                             |   |                                 |

| Storage & handling   | Cutting   |
|--|---|
| Store packs on a clean surface and cover them<br>Process from multiple packs at the same time<br>Follow the Vandersanden processing guidelines | Cutting with power tools may generate dust. This dust may<br>contain silica or quartz particulate which may constitute a<br>hazard. Persons undertaking work of this nature are advised<br>to wear dust masks (FFP3). |

\* All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.